

## Declaration of Performance

(according to regulation EU No 305/2011)

Unique identification of product type:  
**Number: LMB Section & Bar S275J2**

**Bars & Section S275J2 / 1.0145 according EN 10025-2: 2004**

Intended use:  
**Welded, bolted and riveted structures**

Manufacturer:  
**Liberty Merchant Bar plc**  
**Liberty House, P O Box 15**  
**Brigg Road, Scunthorpe**  
**DN16 1XL United Kingdom**

**T: +44 (0) 1724 853333**  
**F: +44 (0) 1724 403044**

**Website:** <http://www.libertysteelscunthorpe.com/>

System of assessment and verification of constancy of performance of the product:  
**System 2+**

Scope as detailed in Certificate of Conformity of  
 Factory Production Control No: **2814/CPR/20060002/A**

Notified factory production control certification body No. 2814 performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificate of conformity of the factory production control


The performance of the product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.



Subhajit Roy Chowdhury  
 Chief Executive Officer  
 GFG Alliance, UK

Date: 25-10-2021

| Essential characteristic           | Performance            |                                       | Harmonised specification                                |     |     |
|------------------------------------|------------------------|---------------------------------------|---|-----|-----|
|                                    |                        |                                       |   |     |     |
| Tolerances on dimensions and shape | Flat Bar               | EN10058                               | EN10025-1 2004  |     |     |
|                                    | Equal & Unequal Angle  | EN 10056-1 & 2                        |   |     |     |
|                                    | Rounds                 | EN 10060                              |   |     |     |
|                                    | Squares                | EN 10059                              |   |     |     |
|                                    | PFC                    | EN 10279                              |   |     |     |
|                                    | I & H Sections         | EN 10034                              |   |     |     |
| Yield strength (longitudinal)      | Nominal thickness (mm) | Values Min (MPa)                      | EN10025-1 2004  |     |     |
|                                    | >                      | ≤                                     |   |     |     |
|                                    | -                      | 16                                    |   | 275 |     |
|                                    | 16                     | 40                                    |   | 265 |     |
|                                    | 40                     | 63                                    |   | 255 |     |
|                                    | 63                     | 80                                    |   | 245 |     |
|                                    | 80                     | 100                                   |   | 235 |     |
| Tensile strength (longitudinal)    | Nominal thickness (mm) | Values (MPa)                          | EN10025-1 2004  |     |     |
|                                    | ≥                      | ≤                                     |   | min | max |
|                                    | 3                      | 100                                   |   | 410 | 560 |
|                                    |                        |                                       |   |     |     |
| Elongation (longitudinal)          | Nominal thickness (mm) | Values min (% , 5.65v <sub>so</sub> ) | EN10025-1 2004  |     |     |
|                                    | >                      | ≤                                     |   |     |     |
|                                    | -                      | 40                                    |   | 22  |     |
|                                    | 40                     | 63                                    |   | 21  |     |
|                                    | 63                     | 100                                   |   | 20  |     |
| Impact strength (longitudinal)     | J2                     | 27J at -20°C                          |   |     |     |
| Weldability CEV                    | Nominal thickness (mm) | Values max (%)                        |   |     |     |
|                                    | >                      | ≤                                     |   |     |     |
|                                    | -                      | 40                                    | 0.40  |     |     |
|                                    | 40                     | 150                                   | 0.42  |     |     |
| Durability                         | Nominal thickness (mm) | Values max (%)                        |   |     |     |
|                                    | -                      | >40                                   | C: 0.18<br>Mn: 1.50<br>P: 0.025<br>S: 0.025<br>Cu: 0.55 |     |     |



2814

EN 10025-1 – 2004

**Bar and Section S275J2 / 1.0145**

To be used in welded, bolted and riveted structures

Elongation:  
 Tensile Strength:  
 Yield Strength: EN10025-2  
 Impact Strength:  
 Weldability:  
 Durability:

Dangerous Substances: No Performance Determined

CE Marking Notified Body:  
 Lloyd's Register Verification B.V.  
 K.P. van der Mandelelaan 41A  
 Rotterdam, Netherlands  
 Phone : +31 (0)10 4145088  
 Email : rotterdam@lr.org

**Liberty Merchant Bar**

